

## HIGH SPECIFICATION AGGREGATES

The specific thresholds used to define HSA and the corresponding values of Gibson's aggregate are summarised below.

Property	Limiting Value	Declared Value
Polished Stone Value (PSV)	$\geq 58$	60+
Aggregate Abrasion Value (AAV)	$\leq 16$	5
Los Angeles Coefficient (LA)	$\leq 30$	13
Magnesium Sulphate Value (MS)	$\leq 25\%$	3